




Test Result for LHMA113

Sample Description	H-P22	Model No:	LHMA113
Date of Test	2020-7-23	Test Person	3
Test Temperature	25	Test Humidity	50
Width of Test Sample(mm)	146	Thickness of Test Sample(mm)	24
Joist Distance(mm)	400	Sectional Area(mm ²)	3473.85
Breaking Load(N)	4044.0	Static Bending Strength(MPa)	29.35
Force Increment(N)	687.5	Bending Increment(mm)	1.81
Slope	380	Modulus of Elasticity(MPa)	3090



ZHEJIANG NEW INSIGHT MATERIAL TECHNOLOGY CO., LTD.
浙江新远见材料科技股份有限公司